



Selection
MILLEFILO

EcoVero™

KISSING A STRANGER Nm 44,5 89%VI Viscose 11%PL Polyester
(71%VI Viscose EcoVero™ 18%VI Recycled Viscose)

IMPIEGO : Ad un filo su macchina rettilinea finezza 18

ISTRUZIONI DI LAVAGGIO : Lavare a mano in acqua tiepida con sapone neutro, oppure a secco con solventi atti allo scopo. I capi non devono essere mai lasciati pressati, ripiegati ed ammucchiati quando sono bagnati o umidi. Non centrifugare prima di aver risciacquato i capi accuratamente. Non torcere mai i capi. I capi devono essere sempre stirati a rovescio oppure tra due panni. La stabilità dimensionale e l'aspetto del capo saranno ottimali solo in seguito al primo lavaggio in acqua. **Per capi rigati a colori contrastanti lavare a secco.**

SIMBOLI DI LAVAGGIO :     

SOLIDITA' : In acqua a 40° C A secco Luce
(valori medi) 3 / 4 4 4

Le solidità dei colori indicati al lavaggio a 40°C sono effettuate in conformità norme UNI EN 20105-1999-C06/ISO 105-A1S ("Degradation") e sono ottenuti eseguendo una media valori della ns. cartella.

RACCOMANDAZIONI : A causa della naturale delicatezza di questo filato, si raccomanda di prestare massima attenzione nel maneggiarlo; la lavorazione va eseguita esclusivamente su macchinari in perfette condizioni e in assenza di asperità che possano causare rotture/degrado/snagging. A causa dell'effetto confort, il filato subisce un assestamento dimensionale durante il lavaggio e la successiva asciugatura. Ciò rende indispensabile effettuare, per ogni bagno, le dovute prove su capi pilota al fine di verificarne i dati medi di rientro. **Per la costruzione del filato, è da considerarsi nella norma una leggera torsione dei teli.** Consigliamo l'utilizzo di questo articolo su macchine a 2 o più guidafilati, per distribuire uniformemente l'effetto. Per le caratteristiche del prodotto uno scarto del 7% è da considerarsi nei costi di tessitura. Raccomandiamo controllare attentamente i teli durante il processo di tessitura e di interrompere immediatamente la lavorazione in caso di evidenti irregolarità. La venditrice non si assumerà nessuna responsabilità per contestazioni derivate da difettosità o incognite del prodotto, che comunque fossero già presenti nel filato campionato. È quindi indispensabile che l'utilizzatore del filato esegua accurati test in fase di campionatura. Non si accettano reclami per quantitativi superiori a 5 Kg di filato smacchinato ed in nessun caso capi finiti e/o confezionati. Non si accetteranno reclami per filato riroccato dall'utilizzatore senza autorizzazione. **I colori di cartella sono soggetti a variazioni da lotto a lotto.** L'uso di detersivi contenenti sbiancanti ottici, altera la tonalità del colore originale. Questo filato è conforme agli standards contemplati dal regolamento REACH.



: colori disponibili per campionatura.

Questo filato non contiene coloranti che possono liberare le ammine vietate nel decreto legislativo tedesco del 15 / 07 / 94

KNITTING INSTRUCTIONS : At 1 ply on 18 gg flat bed machine

CLEANING INSTRUCTIONS : Washing instructions below indicated have to be considered as the limit to maintain yarn's characteristic. Customer must make all necessary tests before labelling garments as suggested. Some parameters may vary because of the stitch, finishing, printing or any other procedure that may modify yarn's structure and of which mill won't be responsible. Garment dimensionality and look will be optimal only after the first washing with neutral soap. **For striped garments with strong and contrasting colours, we recommend dry cleaning only.**

CARE LABEL INSTRUCTIONS :     

COLOUR FASTNESS : Washing at 40 ° C Dry Cleaning Light
3 / 4 4 4

Color fastness values indicated for washing at 40°C are made in accordance with UNI EN 20105-1999-C06/ISO 105-A1S and must be considered as an average for our shade card.

SPECIAL CARES : Being the yarn extremely delicate, it is indispensable to handle it with extreme care; knitting must be done **ONLY** on machines in perfect conditions and avoiding any roughness that can cause breakages/snagging/degradation. We strongly suggest to test each single dyelot to verify the shrinkage because of the confort effect of this quality (causing changes on the dimension stability of the garment during the washing and following drying process) we strongly suggest to test each dyeing lot to verify the shrinkage. **A slight torquing effect must be considered as unavoidable due to the yarn construction.** We recommend to use this yarn on knitting machine with 2 or more threadguides in order to obtain a more even effect. Considering yarn's structure a 7% of waste must be considered as unavoidable and figured in knitting costs. Carefully check knitted panels and immediately stop the knitting in case of defects. Mill will not take any responsibility for claim coming from defects of the product already appreciable on sample yarn: it is indispensable to carefully test the yarn during this phase. Claims for amounts of yarn exceeding kgs.5 will not be accepted, as well as any claim regarding finished garments. It will not be possible to accept claims on yarn "rewound" by customer without authorization. **Colors differences compared to shade card standard may happen.** Using soaps with optical bleaches does change the original color tone. This yarn complies the REACH regulation quality standards.



: colours available for samples.

This quality does not contain dye-stuffs which could set free the amines listed in to the German decree dated 15 / 07 / 94